

(19) World Intellectual Property Organization
International Bureau(43) International Publication Date
8 February 2001 (08.02.2001)

PCT

(10) International Publication Number
WO 01/09059 A1(51) International Patent Classification⁷: C04B 37/00,
37/02, H01M 2/084855 Spirea Ct., West Richland, WA 99353 (US). ARM-
STRONG, Timothy, R.; 6817 W. Wernett Road, Pasco,
WA 99301 (US). PEDERSON, Larry, R.; 4205 S. Toro
Road, Kennewick, WA 99338 (US).

(21) International Application Number: PCT/US00/20534

(22) International Filing Date: 28 July 2000 (28.07.2000)

(74) Agent: MAY, Stephen, R.; Battelle Memorial Institute,
Pacific Northwest Division, Intellectual Property Services,
P.O. Box 999, MSIN: K1-53, Richland, WA 99352 (US).



(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
09/365,343 30 July 1999 (30.07.1999) US
09/562,583 1 May 2000 (01.05.2000) US(81) Designated States (*national*): AE, AG, AL, AM, AT, AU,
AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CR, CU, CZ,
DE, DK, DM, DZ, EE, ES, FI, GB, GD, GE, GH, GM, HR,
HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR,
LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ,
NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM,
TR, TT, TZ, UA, UG, UZ, VN, YU, ZA, ZW.(71) Applicant: BATTELLE MEMORIAL INSTITUTE
[US/US]; Pacific Northwest Division, Intellectual Property
Services, P.O. Box 999, Richland, WA 99352 (US).(84) Designated States (*regional*): ARIPO patent (GH, GM,
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian
patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European
patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE,
IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG,
CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).(72) Inventors: MEINHARDT, Kerry, D.; Apartment R, 2300
Hood, Richland, WA 99352 (US). VIENNA, John, D.;

[Continued on next page]

(54) Title: GLASS-CERAMIC JOINING MATERIAL AND METHOD OF JOINING



(57) Abstract: The present invention is a glass-ceramic material and method of making useful for joining a solid ceramic component and at least one other solid component. The material is a blend of M1-M2-M3, wherein M1 is BaO, SrO, CaO, MgO, or combinations thereof, M2 is Al_2O_3 , present in the blend in an amount from 2 to 15 mol%, M3 is SiO_2 with up to 50 mol% B_2O_3 that substantially matches a coefficient of thermal expansion of the solid electrolyte. According to the present invention, a series of glass ceramics in the M1- Al_2O_3 -M3 system can be used to join or seal both tubular and planar solid oxide fuel cells, oxygen electrolyzers, and membrane reactors for the production of syngas, commodity chemicals and other products.

BEST AVAILABLE COPY

WO 01/09059 A1



Published:

— *With international search report.*

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

GLASS-CERAMIC JOINING MATERIAL AND METHOD OF JOINING

5

FIELD OF THE INVENTION

The present invention is a glass ceramic material and method of making, specifically for use in electrochemical devices such as fuel cells, gas sensors, oxygen or hydrogen pumps/separators, or for sealing any material with a thermal expansion coefficient similar to the seal material.

As used herein, the terms "solid electrolyte" or "solid oxide ion conducting electrolyte" are interchangeable.

As used herein, the term "joint" includes the term "seal" because, in this glass-ceramic field, the "seal" joins at least two parts. However, the "joint" may be intermittent thereby not serving as a "seal".

BACKGROUND OF THE INVENTION

Ceramic materials are being used more often from automobile turbochargers to experimental fuel cells. However, there remains the problem of joining and/or sealing ceramic components to other ceramic components, to metal components, or to combinations thereof (e.g., cermet components) such that the joint maintains integrity during operation. For example, solid oxide ion conducting electrolytes are useful for oxygen separation and high temperature fuel cells. Although many technical challenges of their development have been overcome, there remains the problem of sealing. In a planar design, a gas-tight seal must bond the components together and prevent the mixing of the gas species on both sides of the solid oxide ion conducting electrolyte.

A limited number of materials are suitable as a solid oxide ion conducting electrolyte. The most commonly used materials are yttria stabilized zirconia (YSZ), doped ceria, doped bismuth oxide and doped lanthanum gallate. The thermal expansion coefficient of these materials can range from 10.1×10^{-6} to

14.3 x 10⁻⁶ °C⁻¹ depending on the type of dopant and concentration. The operating temperature can also range from 700°C to 1000°C depending upon which material is chosen as the electrolyte. Therefore, the seal material must be tailored to match the electrolyte thermal expansion, maintain a gas tight seal at temperatures ranging from 200 °C to 1200 °C, and not have detrimental chemical interactions with the fuel cell components. In addition, the seal material must also be stable at the operating temperature (800-1000°C) for extended periods of time (>9,000 hr) and be electrically insulating. For a solid oxide fuel cell, the seal must be able to survive extremely reducing environments.

Various efforts to seal solid oxide ion conducting devices have been made with varying degrees of success. Silica, boron, and phosphate-based glasses and glass-ceramics have been evaluated as a sealing material¹⁻⁴ for solid oxide fuel cells. Experiments conducted by P.H. Larsen et al¹ have shown major problems with glasses purely based on phosphate as the glass former. At temperature, the phosphate volatilized and reacted with the anode to form nickel phosphide and zirconiumoxyphosphate. Additionally, these phosphate glasses usually crystallized to form meta- or pyrophosphates, which exhibited low stability in a humidified fuel gas at the operating temperature.

Borosilicate glasses and glass ceramics have also been considered as potential seal materials. These glasses have been investigated by C. Günther et al² and K.L. Ley et al³ for use in solid oxide fuel cells. However, boron will react with a humidified hydrogen atmosphere to form the gaseous species B₂(OH)₂ and B₂(OH)₃ at the operating temperature². Therefore, any high boron seal may corrode in a humidified hydrogen environment over time. Glasses with B₂O₃ as the only glass former have showed up to a 20% weight loss in the humidified hydrogen environment and extensive interactions with fuel cell component materials both in air and wet fuel gas.¹

Silica-based glasses and glass-ceramics offer the most promise. They typically have a higher chemical resistance and show minimal interaction with the fuel cell component materials.¹ Unfortunately, these glasses tend to have thermal expansions below the range needed for a sealing material.

At the operating temperature, most glasses will crystallize with time. Therefore, it is critical to have a glass composition in which the thermal expansion coefficient after crystallization is compatible with the solid oxide ion conducting electrolyte. Once the glass is fully crystallized, it is typically very stable over time. In addition, crystallized glasses tend to be stronger mechanically at operating temperature, improving seal performance.

Hence, there is a need in the art for a sealing material that can operate at an operating temperature up to about 900°C, has a thermal expansion coefficient between 8×10^{-6} and $15 \times 10^{-6} \text{ }^{\circ}\text{C}^{-1}$, and has no detrimental chemical interactions with the components.

BACKGROUND BIBLIOGRAPHY

1. P.H. Larsen, C. Bagger, M. Mogensen and J.G. Larsen, *Proc. 4th Int. Symp. Solid Oxide Fuel Cells*, Volume 95-1, 1995, pp.69-78.
2. C. Günther, G. Hofer and W. Kleinlein, *Proc. 5th Int. Symp. Solid Oxide Fuel Cells*, Volume 97-18, 1997, pp.746-756.
3. K.L. Ley, M. Krumpelt, R. Kumar, J. H. Meiser, and I. Bloom, *J. Mat. Res.*, Vol. 11, No. 6, (1996) pp. 1489-1493.
4. Yoshinori Sakaki, Masatoshi Hattori, Yoshimi Esaki, Satoshi Ohara, Takehisa Fukui, Kaseki Koderu, Yukio Kubo, *Proc. 5th Int. Symp. Solid Oxide Fuel Cells*, Volume 97-18, 1997, pp.652-660.

SUMMARY OF THE INVENTION

The present invention is a glass-ceramic compound and method of making that are useful in joining or sealing ceramic components to other ceramic components, to metal components, or to combinations thereof (e.g., cermet components). More specifically, the present invention is useful for joining/sealing in an electrochemical cell having at least one solid electrolyte having a first and second side exposed to first and second gas species respectively. The seal is necessary for separating the first and second gas species.

The glass-ceramic compound contains at least three metal oxides, M1-M2-M3. M1 is BaO, SrO, CaO, MgO, or combinations thereof. M2 is Al_2O_3 and is present in the compound in an amount from 2 to 15 mol%. M3 is SiO_2 with up to 50 mol% B_2O_3 . The compound substantially matches a coefficient of thermal expansion of the solid ceramic component and at least one other solid component that is either ceramic, metal, or a combination thereof.

According to the present invention, a series of glass ceramics in the M1- Al_2O_3 -M3 system can be used to join or seal both tubular and planar ceramic solid oxide fuel cells, oxygen electrolyzers, and membrane reactors for the production of syngas, commodity chemicals and other products.

It is an object of the present invention to provide a compound useful for joining or sealing a solid electrolyte or a solid oxide ion conducting electrolyte.

An advantage of a joint/seal made with the compound of M1- Al_2O_3 -M3 is the maintaining of a substantially constant coefficient of thermal expansion from the glass to crystalline phase.

The subject matter of the present invention is particularly pointed out and distinctly claimed in the concluding portion of this specification. However, both the organization and method of operation, together with further advantages and objects thereof, may best be understood by reference to the following description taken in connection with accompanying drawings wherein like reference characters refer to like elements.

BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1 is a phase diagram showing the compositional range of the M1- Al_2O_3 -M3 joint/seal material according to the present invention; and

FIG. 2 is a graph of coefficient of thermal expansion versus temperature for a solid electrolyte and the glass-ceramic material of the present invention.

DESCRIPTION OF THE PREFERRED EMBODIMENT(S)

5 The present invention is a glass-ceramic compound and method of making the glass-ceramic compound. The present invention is useful for joining or sealing between at least two solid ceramic parts, for example a seal in an electrochemical cell having at least one solid electrolyte having a first and second side exposed to first and second gas species respectively. The present invention is also useful for joining or sealing between a solid ceramic component and a metal component or a cermet component. The seal is necessary for separating the first and second gas species during operation, usually at elevated temperatures.

15 The present invention includes a joint between a solid ceramic component and at least one other solid component that is preferably a solid ceramic component, a metal component, or a combination thereof such as a cermet component. The joint has at least three metal oxides of M1-M2-M3. M1 is BaO, SrO, CaO, MgO, or combinations thereof. M2 is Al₂O₃. M3 is SiO₂ with up to 50 mol% B₂O₃. The joint substantially matches a coefficient of thermal expansion of the components comprising the joint. The coefficient of thermal expansion of the joint is from about $7 \times 10^{-6} \text{ }^{\circ}\text{C}^{-1}$ to about $15 \times 10^{-6} \text{ }^{\circ}\text{C}^{-1}$ as measured from 25 °C to 1000 °C.

25 The composition of the joint/seal is preferably in the range wherein M1 is present in an amount from about 20 mol% to about 55 mol%, Al₂O₃ is present in an amount from about 2 mol% to about 15 mol%, and M3 is present in an amount from about 40 mol% to about 70 mol%. The compositional range for the M1- Al₂O₃-M3 system is shown in FIG. 1.

30 The glass-ceramic compound may further contain at least one additional metal oxide including, but not limited to, ZrO₂, TiO₂, Cr₂O₃, and combinations thereof to modify the properties of the glass phase or the final crystallized seal. Properties include, but are not limited to, wetting, glass transition temperature (T_g), glass softening temperature (T_s), thermal expansion coefficient, and combinations thereof.

The range of thermal expansion coefficients for both glass-ceramic and crystallized glass-ceramic is from 7×10^{-6} to $13 \times 10^{-6} \text{ } ^\circ\text{C}^{-1}$. The glass transition temperatures (T_g) and softening temperature (T_s) for the glass-ceramics are in the range of $650^\circ - 800^\circ\text{C}$. However, the crystallized glass-ceramic has a softening temperature above 1000°C .

Substantially the same coefficient of thermal expansion is herein defined as the coefficient of thermal expansion of the seal material within about 30%, preferably within about 16%, more preferably within about 5% of the sealed material.

The joint may be used in an electrochemical test cell to join an oxygen ion pump and a test material. In addition, the joint may be used in an oxygen generator or a fuel cell to join an oxygen ion conducting electrolyte, for example a zirconia electrolyte, and an interconnect, for example manganite, chromite, metal, and combinations thereof.

According to the present invention, a method of joining a solid ceramic component with at least one other solid component has the steps of:

(a) providing a blend of M1, Al_2O_3 , and M3 that substantially matches a coefficient of thermal expansion of a solid ceramic component and at least one other solid component, which is preferably another ceramic component, a metal component, or a combination thereof such as a cermet component. M1 is BaO, SrO, CaO, MgO, or combinations thereof. Al_2O_3 is present in the blend in an amount from 2 to 15 mol%. M3 is SiO_2 with up to 50 mol% B_2O_3 ;

(b) placing said blend at an interface of said solid ceramic component and said at least one other solid component as a pre-assembly;

(c) heating said pre-assembly to a temperature sufficient to cause the blend to flow into and wet the interface as an assembly; and

(d) cooling said assembly and solidifying said blend thereby joining said solid ceramic component and said at least one other solid component.

EXAMPLE 1

An experiment was conducted to demonstrate the glass-ceramic materials (referred to simply as "glass" in Tables E1-1 and E1-2 and **FIG. 2**) of the present invention.

5 Table E1-1 shows several compositions. The major crystallized phases can include $\text{BaO} \cdot 2\text{SiO}_2$, $2\text{BaO} \cdot 3\text{SiO}_2$, $\text{BaO} \cdot \text{SiO}_2$, and $\text{BaO} \cdot \text{Al}_2\text{O}_3 \cdot 2\text{SiO}_2$.

TABLE E1-1. Glass-Ceramic Material Compositions

Glass ID#	Glass Composition (mole%)					
	BaO	SrO	CaO	Al_2O_3	B_2O_3	SiO_2
1	34.8	4.8	----	10.4	----	50.0
3	33.0	5.0	----	7.7	----	54.3
7b	33.7	----	----	10.5	----	55.8
9	36.9	----	----	10.5	----	52.6
10	42.5	----	----	7.5	----	50.0
11	45.0	----	----	5.0	----	50.0
12	41.3	----	----	5.0	----	53.7
13	37.5	----	----	5.0	----	57.5
1d	34.8	----	4.8	10.4	----	50.0
14	30.0	----	10.0	10.0	20.0	30.0
15	25		10	15	15	35
17	20		10	5	30	35
18	35		15	5	10	35

10

FIG. 2 illustrates how well the glass-ceramic material was tailored to match a solid electrolyte. The solid electrolyte material was 8-YSZ and the glass-ceramic compositions were #9 and #14 (i.e., Glass IDs #9 and #14). The thermal expansion of the crystallized glass-ceramic materials was within 0.06% of the expansion of the solid electrolyte material.

15

Table E1-2 shows properties of the glass-ceramic material of the present invention.

20

TABLE E1-2. Glass-Ceramic Material Properties

Glass ID#	Glass Transition Temperature (T _g , °C)	Softening Temperature (T _s , °C)	Thermal Expansion (Glass, 25°C to T _g)	Thermal Expansion (Crystallized Glass, 25°C to 1000°C)
1	700	760	10.3	12.8
3	728	791	9.5	9.2
7b	760	803	8.8	7.6
9	726	803	9.4	10.5
10	736	788	11.2	13.4
11	710	763	11.4	14.6
12	702	749	11.5	12.8
13	695	745	11.1	9.6
1d	738	802	10.0	11.5
1e	720	783	10.4	12.5
14	597	640	9.48	----
15	620	684	7.5	----
17	621	670	7.85	----
18	588	650	10.8	----

5 EXAMPLE 2

Seals formed from a glass frit were used to fabricate sealed 8YSZ oxygen pumps. A zirconia pump of fully dense small closed end tube and test material of flat plate of 8 mol% stabilized zirconia were sealed together with a mixture of 70 wt% glass-ceramic composition #9 and 30 wt% glass-ceramic composition #14 to assemble an electrochemical test cell. The tube was electroded with Pt on both the inside and outside to function as an oxygen pump. Pt leads were connected to the electrodes. The pre-assembly was placed in a furnace, heated to 1150°C to seal. The temperature was reduced after sealing to the crystallization temperature and held there until the seal crystallized. After crystallization, the assembly was allowed to cool to room temperature

The assembly was tested by pumping oxygen out of the sealed assembly and found capable of reaching a partial pressure of oxygen of 1×10^{-18} atm at 1000 °C. An oxygen leak rate of 3.7×10^{-5} standard cubic centimeters per sec

(sccs) was calculated from the pumping current. This is adequate for solid oxide fuel cells and oxygen generators.

CLOSURE

5

While a preferred embodiment of the present invention has been shown and described, it will be apparent to those skilled in the art that many changes and modifications may be made without departing from the invention in its broader aspects. The appended claims are therefore intended to cover all such
10 changes and modifications as fall within the true spirit and scope of the invention.

CLAIMS

We claim:

5

1. A joint between a solid ceramic component and at least one other solid component, said joint comprising:

at least three metal oxides of M1-M2-M3 combined together wherein M1 is selected from the group consisting of BaO, SrO, CaO, MgO, and combinations thereof, M2 is Al_2O_3 wherein M2 is present in an amount from 2 to 15 mol%, and M3 is SiO_2 with up to 50 mol % of B_2O_3 , said joint substantially matching a coefficient of thermal expansion of said solid ceramic component and said at least one other solid component.

15

2. The joint as recited in claim 1, wherein said at least one other solid component is ceramic.

20

3. The joint as recited in claim 1, wherein said at least one other solid component is metal.

4. The joint as recited in claim 1, wherein said at least one other solid component is cermet.

25

5. The joint as recited in claim 1 that is a seal.

6. The joint as recited in claim 1 wherein said coefficient of thermal expansion is from about $7 \times 10^{-6} \text{ }^\circ\text{C}^{-1}$ to about $15 \times 10^{-6} \text{ }^\circ\text{C}^{-1}$ as measured from 25 $^\circ\text{C}$ to 1000 $^\circ\text{C}$.

30

7. The joint as recited in claim 1, wherein said M1 is present in an amount from about 20 mol% to about 55 mol% and said M3 is present in an amount from about 40 mol% to about 70 mol%.

8. The joint as recited in claim 1, further comprising at least one additional metal oxide.

9. The joint as recited in claim 8, wherein said at least one additional metal oxide is selected from the group consisting of ZrO_2 , TiO_2 , Cr_2O_3 , and combinations thereof.

10. The joint as recited in claim 1, wherein said solid ceramic component and said at least one other solid component are an oxygen ion pump and a test material in an electrochemical test cell.

11. The joint as recited in claim 1, wherein said solid ceramic component and said at least one other solid component are an oxygen ion conductor and an interconnect in an oxygen generator.

15

12. The joint as recited in claim 1, wherein said solid ceramic component and said at least one other solid component are an oxygen ion conductor and an interconnect in a fuel cell.

20 13. A method of joining a solid ceramic component and at least one other solid component, comprising the steps of:

(a) providing a blend of M1-M2-M3 wherein M1 is selected from the group consisting of BaO , SrO , CaO , MgO , and combinations thereof, M2 is Al_2O_3 , wherein M2 is present in an amount from 2 to 15 mol%, and M3 is SiO_2 with up to 50 mol % of B_2O_3 , that substantially matches a coefficient of thermal expansion of said solid ceramic component and said at least one other solid component;

25

(b) placing said blend at an interface of said solid ceramic component and said at least one other solid component as a pre-assembly;

30

(c) heating said pre-assembly to a temperature sufficient to cause the blend to flow into said interface as an assembly; and

(d) cooling said assembly and solidifying said blend thereby joining said solid ceramic component and said at least one other solid component.

5 14. The method as recited in claim 13, wherein said joining is sealing.

 15. The method as recited in claim 13, wherein said coefficient of thermal expansion is from about $7 \times 10^{-6} \text{ }^{\circ}\text{C}^{-1}$ to about $15 \times 10^{-6} \text{ }^{\circ}\text{C}^{-1}$ as measured from 25 $^{\circ}\text{C}$ to 1000 $^{\circ}\text{C}$.

10

 16. The method as recited in claim 13, wherein said M1 is present in an amount from about 20 mol% to about 55 mol% and said M3 is present in an amount from about 40 mol% to about 70 mol%.

15 17. The method as recited in claim 13, further comprising at least one additional metal oxide.

 18. The method as recited in claim 17, wherein said at least one additional metal oxide is selected from the group consisting of ZrO_2 , TiO_2 , Cr_2O_3 , and combinations thereof.

20




 19. The method as recited in claim 13, wherein said solid ceramic component and said at least one other solid component are an oxygen ion pump and a test material in an electrochemical test cell.

25

 20. The method as recited in claim 13, wherein said solid ceramic component and said at least one other solid component are an oxygen ion conductor and an interconnect in a fuel cell.

30

 21. The joint as recited in claim 13, wherein said solid ceramic component and said at least one other solid component are an oxygen ion conductor and an interconnect in an oxygen generator.

*Fig. 1**Fig. 2*

INTERNATIONAL SEARCH REPORT

national Application No

PCT 00/20534

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C04B37/00 C04B37/02 H01M2/08

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C04B H01M

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, PAJ

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	PATENT ABSTRACTS OF JAPAN vol. 9, no. 89 (E-309), 18 April 1985 (1985-04-18) -& JP 59 219850 A (MITSUBISHI DENKI KK), 11 December 1984 (1984-12-11) abstract; table 1 ---	1-9, 13-18
X	GB 1 019 821 A (PHILIPS ELECTRONIC AND ASSOCIATED INDUSTRIES LTD.) 9 February 1966 (1966-02-09) claims 1-7; tables 2-4 ---	1-5, 7, 8, 13, 14, 16, 17
X	EP 0 220 813 A (THORN EMI PLC) 6 May 1987 (1987-05-06) page 6, line 4 - line 5; claims 1-4, 6 --- -/--	1-5, 7-9, 13, 14, 16-18



Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

* Special categories of cited documents:

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- "&" document member of the same patent family

Date of the actual completion of the international search

4 October 2000

Date of mailing of the international search report

13/10/2000

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Hauck, H

INTERNATIONAL SEARCH REPORT

national Application No

PCT/00/20534

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 0 055 049 A (THORN EMI PLC) 30 June 1982 (1982-06-30) claims 1-9,12,13,16-18; tables 1-3 ---	1-5,7-9, 13,14, 16-18
X	EP 0 351 097 A (THORN EMI PLC) 17 January 1990 (1990-01-17) claims 1,8,9 ---	1-5,7-9, 13,14, 16-18
X	DE 31 34 739 A (NGK INSULATORS LTD.) 1 April 1982 (1982-04-01) claims 1,3; table 1 ---	1,2,5, 7-9,13, 14,16-18
X	K.L. LEY ET AL.: J. MATER. RES., vol. 11, no. 6, June 1996 (1996-06), pages 1489-1493, XP000951437 cited in the application table 1 ---	1-8,12
X	C. GÜNTHER ET AL.: ELECTROCHEMICAL PROCEEDINGS, vol. 97-18, 1997, pages 746-756, XP000951506 cited in the application table 1 -----	1,2,5

INTERNATIONAL SEARCH REPORT

Information on patent family members

National Application No

PCT 00/20534

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
JP 59219850	A	11-12-1984	NONE	
GB 1019821	A		NONE	
EP 220813	A	06-05-1987	DE 3688672 A	12-08-1993
			DE 3688672 T	21-10-1993
			HU 41557 A, B	28-04-1987
			JP 1993282 C	22-11-1995
			JP 7011947 B	08-02-1995
			JP 62058563 A	14-03-1987
EP 55049	A	30-06-1982	CA 1168291 A	29-05-1984
			DE 3174149 D	24-04-1986
			JP 1058829 B	13-12-1989
			JP 1577251 C	24-08-1990
			JP 57126058 A	05-08-1982
			US 4585972 A	29-04-1986
			US 4694219 A	15-09-1987
EP 351097	A	17-01-1990	JP 2133335 A	22-05-1990
			US 5099174 A	24-03-1992
DE 3134739	A	01-04-1982	JP 1248001 C	16-01-1985
			JP 57047777 A	18-03-1982
			JP 59020632 B	14-05-1984
			US 4451516 A	29-05-1984

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

☐ BLACK BORDERS

☒ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES

☐ FADED TEXT OR DRAWING

☒ BLURRED OR ILLEGIBLE TEXT OR DRAWING

☐ SKEWED/SLANTED IMAGES

☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS

☐ GRAY SCALE DOCUMENTS

☐ LINES OR MARKS ON ORIGINAL DOCUMENT

☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY

☐ OTHER: _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.